

Ultramid® 8272GHS BK102

Polyamide 6

Ultramid 8272GHS BK102 is a 12% glass fiber reinforced, black pigmented, thermally modified, PA6 blow molding compound offering an excellent balance of engineering properties combined with the melt strength ideally suited for blow molding and other applications requiring ultra high melt viscosity. It exhibits improved strength, stiffness and creep resistance compare to standard blow molding grades. Outstanding permeability and chemical resistance to oils, hydrocarbons and most solvents are other advantages along with excellent stiffness ad the ability to fabricate complex shapes for cost effective metal replacements.

Applications

Ultramid 8272GHS BK102 is designed for blow molding applications requiring improved short term thermal performance as well as extrusions. It is ideal for air ducts, reservoirs and covers.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm ³	1183	1.22	
Moisture, %	62		
(24 Hour)		1.4	
(50% RH)		2.3	
(Saturation)		8.3	
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
-40°C		6,370	6,400
23°C		5,220	3,100
80°C		2,100	1,900
120°C		1,445	1,500
150°C		1,470	1,400
Tensile stress at break, MPa	527		
-40°C		115	110
23°C		110	60

120°C		45	25
150°C		40	25
Tensile strain at break, %	527		
-40°C		2.0	2.0
23°C		3.0	-
120°C		15	20
150°C		12.5	15
Flexural Modulus, MPa	178		
23°C		4,300	-
IMPACT	ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m²	180		
23°C		5.9	-
Charpy Notched, kJ/m²	179		
23°C		7.1	-
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, °C	3146	220	-
HDT A, °C	75	170	-
HDT B, °C	75	210	-
Coef. of Linear Thermal Expansion, Parallel, mm/mm °C		0.28 X10-4	-
Coef. of Linear Thermal Expansion, Normal, mm/mm °C		0.72 X10-4	-
ELECTRICAL	ISO Test Method	Dry	Conditioned
Volume Resistivity (Ohm-m)	IEC 60093	>1E13	>1E13

Processing Guidelines

Material Handling

Max. Water content: 0.15%

Material is supplied in sealed containers and drying prior to molding in a dehumidifying or desiccant dryer is recommended. Drying parameters are dependent upon the actual percentage of moisture in the pellets and typical pre-drying conditions are 2-4 hours at 180F (83C). Further information concerning safe handling procedures can be obtained from the Safety Data Sheet

(MSDS), or by contacting your BASF representative.

Typical Profile

Melt Temperature 245-260°C (473-500°F)

Mold Temperature 60°C (140°F)

Blow Ratio 2:1

Mold Temperatures

Mold temperatures of 60°C (140°F) are generally recommended; however, surface temperatures of 10-95°C (50-203°F) can be used where applicable. The degree of crystallinity of thin polyamide wall sections, 0.6mm (.023") or less, may be controlled by the temperature of the mold. A cold mold, 5-30°C (41-86°F), will rapidly quench the section producing a clear, relatively flexible part, while a hot mold, over 40°C (104°F), will produce an opaque part with increased stiffness.

Blow Ratio

A diametrical blow ratio of 2:1 is generally recommended for plain symmetrical parts. As part complexity increases, lower blow ratios should be utilized to prevent thin wall cross sections, especially in corners.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

BASF Corporation

Engineering Plastics
1609 Biddle Avenue
Wyandotte, MI 48192



General Information

800-BC-RESIN

Technical Assistance

800-527-TECH (734-324-5150)

Web address

<http://www.plasticsportal.com/usa>