

Ultramid® 8350 HS

Polyamide 6

Ultramid 8350 HS is a heat stabilized, impact modified type 6 graft copolymer developed for extrusion, tubing, and jacketing applications requiring a high level of toughness combined with a moderate level of flexibility. It is also available in non-heat stabilized (Ultramid 8350) and/or pigmented versions.

Applications

Ultramid 8350 HS is generally recommended for applications such as automotive vacuum tubing, cable jacketing, and high pressure and hydraulic hoses.

PHYSICAL	ISO Test Method	Property Value
Density, g/cm ³	1183	1.07
Moisture, %	62	
(24 Hour)		1.1
(50% RH)		1.9
(Saturation)		6.7

MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
-40°C		2,150	-
23°C		1,800	675
80°C		210	-
120°C		150	-
150°C		130	-
Tensile stress at yield, MPa	527		
-40°C		85	95
23°C		53	32
80°C		20	-

120°C		14	-
150°C		9	-
Tensile strain at yield, %	527		
23°C		5	9
Nominal strain at break, %	527		
23°C		>50	>50
Flexural Strength, MPa	178		
23°C		50	-
Flexural Modulus, MPa	178		
23°C		1,750	-
IMPACT	ISO Test Method	Dry	Conditioned
Charpy Notched, kJ/m²	179		
-30°C		15	-
23°C		100	-
Charpy Unnotched, kJ/m²	179		
23°C		N	-
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, °C	3146	220	-
HDT A, °C	75	51	-
HDT B, °C	75	145	-
ELECTRICAL	ISO Test Method	Dry	Conditioned
Comparative Tracking Index	IEC 60112	600	-
Volume Resistivity (Ohm-m)	IEC 60093	>1E13	-
UL RATINGS	UL Test Method	Property Value	
Flammability Rating, 1.5mm	UL94	HB	
Relative Temperature Index, 1.5mm	UL746B		

Mechanical w/o Impact, °C		65
Mechanical w/ Impact, °C		65
Electrical, °C		65
Flammability Rating, 3.0mm	UL94	HB
Relative Temperature Index, 3.0mm	UL746B	
Mechanical w/o Impact, °C		65
Mechanical w/ Impact, °C		65
Electrical, °C		65

Processing Guidelines

Material Handling

Max. Water content: 0.1%

Material is supplied in sealed containers and drying prior to molding in a dehumidifying or desiccant dryer is recommended.

Drying parameters are dependent upon the actual percentage of moisture in the pellets and typical pre-drying conditions are 2-4 hours at 180F (83C). Further information concerning safe handling procedures can be obtained from the Safety Data Sheet (MSDS), or by contacting your BASF representative.

Typical Profile

Melt Temperature 240-250°C (464-482°F)

Typical Barrel Profile (°C):

Rear 245-260°C (473-500°F)
 Middle 240-255°C (464-491°F)
 Front 240-250°C (464-482°F)

Head 225-245°C (437-473°F)
 Flange 225-240°C (437-464°F)
 Die 225-240°C (437-464°F)

Screw Parameters

Metering Section	40%
Transition Section	6 to 7 flights
Feed Section	balance of screw length
Compression Ratio	3.5:1 to 4.0:1
L/D Ratio	20:1 to 24:1

Tooling & Sizing

Die to Finished Tube dia. 1.5-2.0:1

Selection of pin and die size will be dependent on the material viscosity. In general, the ratio of die size to finished tube diameter is about 1.5-2.0:1. The mandrel (pin) size is determined the same way in relation to the inner tube diameter.

Free (open tank) extrusion is recommended when producing tube diameters 1 cm and below. For larger diameters, a differential pressure vacuum tank is recommended.

Tooling draw ratio is generally higher with free extrusion versus sizing, however will depend on melt viscosity. The vacuum sizer entrance should be about 3-9% larger than the finished tube outer diameter. Selection will depend on melt viscosity and die swell of the extrudate.

Quenching

For diameters less than or equal to 1 cm (.39") O.D., open tank quenching with normal tap water is suggested. Depending upon line speed, quenching distance can vary from 7.5 to 12 meters (24.6-39.4 feet). A short air gap (die to quench water) is recommended for both tubing and cable jacketing for best flexibility.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

BASF Corporation

Engineering Plastics
1609 Biddle Avenue
Wyandotte, MI 48192



General Information

800-BC-RESIN

Technical Assistance

800-527-TECH (734-324-5150)

Web address

<http://www.plasticsportal.com/usa>