

Ultramid® A3EG7 BK23189 Polyamide 66

Ultramid A3EG7 BK23189 is a 35% glass fiber reinforced, pigmented black, injection molding PA66 grade for machinery components and housings of high stiffness and dimensional stability.

Applications

Typical applications include lamp socket housings, cooling fans, insulating profile for aluminium window frames, water containers for automotive cooling systems, as well as electrically insulating parts.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm ³	1183	1.42	
Moisture, %	62		
(50% RH)		1.6	
(Saturation)		5	
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
23°C		11,000	-
Tensile stress at break, MPa	527		
23°C		198	-
Tensile strain at break, %	527		
23°C		2.6	-
Flexural Modulus, MPa	178		
23°C		10,400	-
IMPACT	ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m²	180		
-40°C		8	-
23°C		9	-

Charpy Notched, kJ/m²	179		
-30°C		9	-
23°C		9	-
Charpy Unnotched, kJ/m²	179		
-30°C		54	-
23°C		62	-
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, °C	3146	260	-
HDT A, °C	75	250	-

Processing Guidelines

Material Handling

Max. Water content: 0.15%

Material is supplied in sealed containers and drying prior to molding in a dehumidifying or desiccant dryer is recommended. Drying parameters are dependent upon the actual percentage of moisture in the pellets and typical pre-drying conditions are 2-4 hours at 180F (83C). Further information concerning safe handling procedures can be obtained from the Safety Data Sheet (MSDS), or by contacting your BASF representative.

Typical Profile

Melt Temperature 280-305°C (536-581°F)

Mold Temperature 80-90°C (176-194°F)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

Mold Temperatures

A mold temperature of 80-90°C (176-194°F) is recommended, however temperatures of as low as 45°C (113°F) and as high as 105°C (221°F) can be used where applicable.

Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR

DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

BASF Corporation

Engineering Plastics
1609 Biddle Avenue
Wyandotte, MI 48192



General Information

800-BC-RESIN

Technical Assistance

800-527-TECH (734-324-5150)

Web address

<http://www.plasticsportal.com/usa>